Research Paper

Enhanced Photosensitivity in Monolayer MoS₂ with PbS Quantum Dots

Sangeun Cho^a, Yongcheol Jo^a, Hyeonseok Woo^a, Jongmin Kim^a, Jungwon Kwak^b, Hyungsang Kim^a, and Hyunsik Im^{a*}

^a Division of Physics & Semiconductor Science, Dongguk University, Seoul 04620, South Korea

^b Medical Physics Department, Asan Medical Center, Seoul 05505, South Korea

Received March 28, 2017; revised April 27, 2017; accepted April 27, 2017

Abstract Photocurrent enhancement has been investigated in monolayer (1L) MoS₂ with PbS quantum dots (QDs). A metal-semiconductor-metal (Au-1L MoS₂-Au) junction device is fabricated using a standard photolithography method. Considerably improved photo-electrical properties are obtained by coating PbS QDs on the Au-1L MoS₂-Au device. Time dependent photoconductivity and current-voltage characteristics are investigated. For the QDs-coated MoS₂ device, it is observed that the photocurrent is considerably enhanced and the decay life time becomes longer. We propose that carriers in QDs are excited and transferred to the MoS₂ channel under light illumination, improving the photocurrent of the 1L MoS₂ channel. Our experimental findings suggest that two-dimensional layered semiconductor materials combined with QDs could be used as building blocks for highly-sensitive optoelectronic detectors including radiation sensors.

Keywords: Photodetector, Molybdenum disulfide, PbS quantum dot

I. Introduction

Two-dimensional materials such as transition metal dichalcogenides (TMDCs) that consist of layered structures have received enormous attention [1,2]. In particular, TMDCs' properties for the absorption and emission of photons can be exploited in solar cell arrays, wearable electronics, and transparent displays [3,4,5]. One prominent candidate material for optoelectronic devices is monolayer MoS₂, which offers a direct bandgap of 1.9 eV. Because of its unique optoelectronic properties and mechanical stability, it could be suitable for applications in optoelectronic devices [6,7]. However, the photo-responsivity and the sensitivity of monolayer MoS₂ are relatively low, and are poor compared with graphene-based photo-electronic devices [8].

For applications of high sensitive optoelectronics, emerging devices consisting of quantum dots (QDs) combined with graphene or atomically-thin MoS₂ have been demonstrated showing high gain and optical sensitivity [9,10]. In this study, we demonstrate a highly sensitive photodetector with 1L-MoS₂ coated with PbS QDs. We observe that the photocurrent and life time of a metal-1L MoS₂-metal device is improved by coating QDs on the 1L MoS₂.

II. Experiment

A monolayer MoS₂ film on SiO₂ was provided by the Professor Cha group at Oxford. The size of the MoS₂ flakes is on the order of several tens of micrometers. The MoS₂ flakes were grown by a conventional chemical vapor deposition method. Figure 1(a) shows an optical image of the MoS₂ flakes on the SiO₂ substrate. Fig. 1(b) shows the Raman spectrum confirming that the MoS₂ flake is a monolayer. The Raman spectrum exhibits two strong peaks: one is the in-plane E_{2g}¹ (~384 cm⁻¹) and the other is the out-of-plane A_{1g} (~403 cm⁻¹). The difference Δk between them is approximately 19 cm⁻¹, confirming that the MoS₂ flakes are predominantly one monolayer thick.

1. Device Fabrication

A conventional photo-lithography process was used to fabricate symmetric Au-1L MoS₂-Au junction devices on a SiO₂ substrate. The MoS₂/SiO₂/Si substrate was coated with a promoter and a photoresist (AZ 5214E) by using a spin coater (MIDAS, SPIN -1200D). Pre-coating was carried out at 1200 rpm for 10 seconds and the main coating was deposited at 5500 rpm for 1 minute. The uniformity of the photoresist layer is enhanced during this process. A hot plate was then used to perform soft-baking (pre-baking) for 50 seconds at 115°C. After the soft-baking process, UV light (wavelength: 350-450 nm, model: MIDAS, MDA-400M) was exposed for 7 seconds on the photoresist to make a device pattern, followed by a post-baking process at 115°C for 2 minutes. The exposure

*Corresponding author
E-mail: hyunsik7@dongguk.edu

Figure 1. (a) Optical image and (b) Raman spectrum of MoS₂ flakes on a SiO₂/Si substrate. In the Raman spectrum, the frequency difference between the main peaks is 19.3 cm⁻¹, confirming the MoS₂ flake is one monolayer thick.

process was then performed again for 10 seconds without the mask.

To make a desired pattern, the sample was immersed in a developer solution for 1 minute and cleaned in methanol and deionized (DI) water for 1 minute. After the desired pattern was formed on the MoS₂/SiO₂, metal deposition was carried out to make electrodes. Metal contacts were fabricated by thermal evaporation of Cr (20 nm) and Au (180 nm), respectively. Finally, acetone was used for lift off. The sample was then washed in DI water and dried using dry nitrogen gas. A schematic diagram of the fabrication process is shown in Fig. 2(a).

2. Method of PbS Quantum dots (QDs) coating

To coat PbS QDs on the MoS₂ channel layer sandwiched between the Au electrodes, a PbS QD solution was spin-coated onto the device at 3000 rpm for 15 seconds. Ligand solutions (tetrabutylammonium iodide) were applied for 30 seconds and then spun at 3000 rpm for 10 seconds. In order to remove impurity substance, the device was washed twice in methanol. To uniformly disperse the QDs on the surface, the spin-coating process was repeated 10 times.

3. Measurement of electrical properties

Figs. 2(a) and 2(b) show the fabrication method and an optical image of the Au-1L MoS₂-1L device, respectively. To measure the electrical properties (current-voltage characteristics), conventional 2-terminal transport

Figure 2. (a) Fabrication procedure and (b) optical image of Au-1L MoS₂-Au junction devices. (c) and (d) AFM images of 1L MoS₂ before and after coating the PbS quantum dots.

measurements were performed using a parameter analyzer (Keithley 4200-SCS). The bias-voltage ranged between -0.4 V and +0.4 V with an interval of 0.05 V. In order to measure the photocurrent characteristics of the device, a light controller (ILLUMINATOR KS-100H) was used in a dark box. The current-voltage characteristics of the device were measured at 0 Lux (light off), 1×10^4 Lux, 13×10^4 Lux.

III. Results and Discussion

Atomic force microscopy (AFM) images of MoS₂ with and without PbS QDs are presented in Figs. 2 (c) and (d). The morphology of the MoS₂ differs before and after coating the QDs.

Figure 3(a) shows the measured current-voltage characteristics of the Au-1L MoS₂-Au device without the QDs under different illumination intensities. As the intensity becomes stronger, the photo-current also increases. Figure 3(b) shows the time-dependent photo-response of the 1L-MoS₂ device without the QDs. The current was measured at a bias-voltage of 0.1 V with a laser intensity of 1×10^4 Lux. The laser pulse duration time was 15 seconds. When the laser was off, the photo-current decayed very rapidly.

The current-voltage characteristics of the QDs-coated 1L MoS₂ device measured under the same conditions are shown in Fig. 3(c). With the QDs, the photocurrent is considerably increased. This is presumably because electrons are transferred from the PbS QDs to the MoS₂ channel. Furthermore, the time-dependent photo-response of the Au-QDs-coated 1L MoS₂-Au device shows a considerably improved decay time, as shown in Fig. 3(d). These experimental findings suggest that hybridization of 2D layered semiconductors and quantum dots might be useful to improve the photo-electrical performance of the detectors and sensors.

Figure 3. (a) and (b) Current-voltage characteristics and time-dependent photo-response of an Au-1L MoS₂-Au device, respectively. (c) and (d) Current-voltage characteristics and time-dependent photo-response of an Au-1L MoS₂/PbS QDs-Au device, respectively.

IV. Conclusions

In order to investigate the effect of QDs on the optoelectrical properties of monolayer MoS₂, two different MoS₂ devices, Au-1L MoS₂-Au and Au-QD-coated 1L MoS₂-Au, were fabricated on SiO₂/Si substrates. We found that QDs improve the photo-current and the decay time in the 1L MoS₂, resulting in enhanced sensitivity. Our experimental findings suggest that 0D-2D hybrid devices are a promising device configuration for the next-generation optoelectronics devices for high-sensitivity detectors.

Acknowledgements

This work was supported by the National Research Foundation (NRF) of Korea (Grant Nos. 2015M2A2A6A 02045252 and 2015M2A2A6A 02045253). We would like to thank Prof. Cha at Oxford for providing MoS₂ and PbS quantum dots.

References

- [1] Y. Zhang, H. Li, L. Wang, H. Wang, X. Xie, S. Zhang, R. Liu, and Z. Qiu, Photothermoelectric and photovoltaic effects both present in MoS₂, *Sci. Rep.* 5, 7938 (2015).
- [2] A. Chernikov, T. Berkelbach, H. Hill, A. Rigosi, Y. Li, O. Aslan, D. Reichman, M. Hybertsen, and T. Heinz, Exciton binding energy and nonhydrogenic Rydberg series in monolayer WS₂, *Phys. Rev. Lett.* 113 076802 (2014).
- [3] G.D. Scholes, And G. Rumbles, Excitons in nanoscale systems, *Nature Mater.* 5 683 (2006).
- [4] C.R. Dean, A.F. Young, I. Meric, C. Lee, L. Wang, S. Sorgenfrei, K. Watanabe, T. Taniguchi, P. Kim, K.L. Shepard, and J. Hone, Boron nitride substrates for high quality graphene electronics, *Nature Nanotech.* 5 722 (2010).
- [5] M. Xu, T. Liang, M. Shi, and H. Chen, Graphene-like two dimensional materials, *Chem. Rev.* 113 3766 (2013).
- [6] B. Radisavljevic, and A. Kis, Mobility engineering and a metal-insulator transition in monolayer MoS₂, *Nature Mater.* 12 815 (2013).
- [7] A. Splendiani, L. Sun, Y. Zhang, T. Li, J. Kim, C. Chim, G. Galli, and F. Wang, Emerging photoluminescence in monolayer MoS₂, *Nano Lett.* 10 1271 (2010).
- [8] O. Lopez-Sanchez, D. Lembke, M. Kayci, A. Radenovic, and A. Kis, Ultrasensitive photodetectors based on monolayer MoS₂, *Nature Nanotech.* 8 497 (2013).
- [9] D. Kufer, I. Nikitskiy, T. Lasanta, G. Nabickaite, F. Koppens, and G. Konstantatos, Hybrid 2D-0D MoS₂-PbS quantum dot photodetector, *Adv. Mater.* 6 5635 (2012).
- [10] G. Konstantatos, M. Badioli, L. Gaudreau, J. Osmond, M. Bernechea, F.P. Garcia de Arquer, F. Gatti, and F.H.L. Koppens, Hybrid graphene-quantum dot phototransistors with ultrahigh gain, *Nat. Nanotechnol.* 7 363 (2012).